

What is claimed is:

1. A process for sintering polyethylene having a weight average molecular
5 weight of more than 1,000,000 g/mol, said process comprising:
 - (a) at least partly disentangling said polyethylene;
 - (b) heating the at least partly disentangled polyethylene to a temperature
between room temperature and the crystalline melting temperature of the
polyethylene;
 - 10 (c) compacting the at least partly disentangled polyethylene at a temperature
between room temperature and the crystalline melting temperature of the
polyethylene;
 - (d) heating the compacted polyethylene to a temperature above its crystalline
melting temperature;
 - 15 (e) cooling the polyethylene to a temperature below its crystalline melting
temperature.
2. The process of claim 1, wherein said at least partly disentangling is effected
by a process comprising swelling said polyethylene.
- 20 3. The process of claim 1, wherein said weight average molecular weight is
more than 2,000,000 g/mol.
4. The process of claim 1, wherein said weight average molecular weight is
25 more than 5,000,000 g/mol.

5. The process of claim 1, wherein said weight average molecular weight is more than 10,000,000 g/mol.
6. The process of claim 1, wherein said weight average molecular weight is in the range of 2,000,000-10,000,000 g/mol.
7. The process according to any one of claims 1-6, wherein said polyethylene has a polydispersity of less than 100.
8. The process according to any one of claims 1-6, wherein said polyethylene has a polydispersity of less than 50.
9. The process according to any one of claims 1-6, wherein said polyethylene has a polydispersity of less than 20.
10. The process according to any one of claims 1-6, wherein said polyethylene has a polydispersity of less than 10.
11. The process according to any one of claims 1-10, wherein said polyethylene comprises less than 10 wt% comonomer.
12. The process according to any one of claims 1-10, wherein said polyethylene comprises up to 5 wt% comonomer.
13. The process according to any one of claims 1-12, wherein said polyethylene has a melting temperature of at least 115 °C.

14. The process according to any one of claims 1-12, wherein said polyethylene has a melting temperature of at least 135 °C.
- 5 15. The process according to any one of claims 1-14, wherein said process comprises subjecting said compacted polyethylene to a temperature above its crystalline melting temperature for not more than 60 minutes.
- 10 16. The process according to any one of claims 1-14, wherein said process comprises subjecting said compacted polyethylene to a temperature above its crystalline melting temperature for not more than 45 minutes.
- 15 17. The process according to any one of claims 1-14, wherein said process comprises subjecting said compacted polyethylene to a temperature above its crystalline melting temperature for not more than 15 minutes.
- 20 18. The process according to any one of claims 1-14, wherein said process comprises subjecting said compacted polyethylene to a temperature above its crystalline melting temperature for not more than 5 minutes.
19. The process according to any one of claims 1-18, wherein said temperature between room temperature and the crystalline melting temperature in steps (b) and (c) is at least 60°C.

20. The process according to any one of claims 1-18, wherein said temperature between room temperature and the crystalline melting temperature in steps (b) and (c) is at least 75°C.

5 21. The process according to any one of claims 1-18, wherein said temperature between room temperature and the crystalline melting temperature in steps (b) and (c) is at least 100°C.

10 22. The process according to any one of claims 1-18, wherein said polyethylene is compacted in step (c) at a pressure in the range of 10-200 MPa.

23. The process according to any one of claims 1-22, wherein said temperature above its crystalline melting temperature in step (d) is below 250°C.

15 24. The process according to any one of claims 1-22, wherein said temperature above its crystalline melting temperature in step (d) is below 190°C.

20 25. The process according to any one of claims 1-24, wherein said process further comprises post-treating said polyethylene after at least steps (a)-(d).

26. The process according to claim 25, wherein said post-treating includes crosslinking said polyethylene.

25 27. An article obtained by the process according to any one of claims 1-26.

28. The article of claim 27, wherein said article has a wear coefficient of less than $3.5 \cdot 10^{-4} \text{ mm}^3/\text{mN}$.
- 5 29. The article of claim 27, wherein said article has a wear coefficient of less than $2.5 \cdot 10^{-4} \text{ mm}^3/\text{mN}$.
30. The article of claim 27, wherein said article has a wear coefficient of less than $2.2 \cdot 10^{-4} \text{ mm}^3/\text{mN}$.
- 10 31. The article of claim 27, wherein said article has a wear coefficient of less than $2.0 \cdot 10^{-4} \text{ mm}^3/\text{mN}$.
32. The article according to any one of claims 27-31, wherein said article has a yield strength of at least 5 MPa.
- 15 33. The article according to any one of claims 27-31, wherein said article has a yield strength of at least 20 MPa.
34. The article according to any one of claims 27-33, wherein said article has a tensile strength of at least 10 MPa.
- 20 35. The article according to any one of claims 27-33, wherein said article has a tensile strength of at least 40 MPa.
- 25 36. The article according to any one of claims 27-35, wherein said article has an elongation at break of at least 30%.

37. An article obtained by subjecting polyethylene having a weight average molecular weight above 1,000,000 g/mol to a temperature above its melting temperature for a time less than 60 minutes, wherein said article has a wear coefficient of less than $3.5 \cdot 10^{-4} \text{ mm}^3/\text{mN}$.

5

38. The article according to any one of claims 27-37, wherein said article is selected from the group consisting of artificial implants and orthopedic implants.

- 10 39. The article according to any one of claims 27-37, wherein said article is a sliding part.

40. Polyethylene having a weight average molecular weight of at least 1,000,000 g/mol and highly beneficial sintering characteristics.

15

41. A composition comprising the polyethylene of claim 40.